

CMPL8648 PET Window Laminate Gloss 1.5mil

38 micron (1.5 mil) clear PET face film, solvent based clear acrylic permanent adhesive, 25 micron (1.0 mil) PET liner. Outdoor durable. Gloss finish. For use on window perf / one-way vision films, indoors and out. Can be cleaned with most commercially available non-abrasive cleansers. Provides UV protection extension of 1-2 years, depending on severity of exposure, compared to unlaminated graphics.

USEFUL INFORMATION

Parameter	Test Method	Value
Face Film	ASTM D645	38 μ (1.5 mil) clear PET
Surface Finish / Gloss Level	ASTM D523	Gloss 60° / 95
PVC Elongation at Break	ASTM D882-02	n/a
Liner Caliper		25 μ (1.0 mil)
Liner Type		Single side silicon coated PET
Adhesive		Acrylic, clear permanent (CP), solvent
Initial Tac (180° peel, 20 min,ss)		11 N / 25 mm
Peel Strength (24 hour)	ASTM D882-02	14 N / 25 mm
Shelf Time		24 months
Recommended Minimum Application Temp		depends on laminating machine
Service Temperature Range		-20°C to 65°C (-4F to 150F)
Outdoor Durability		up to two (2) years depending on exposure
UV Protection Extension Factor		1-2 years compared to unlaminated graphic

APPLICATION COMPATIBILITY

Parameter	Range	Other Factors
Typical Applications	Window perf and /or one-way vision films, with or without adhesive. Optically clear PET and adhesive, and smoothness of PET release liner give minimal haze through the open, unprinted areas of the graphic. Prevents dirt from accumulating in the perforations.	
Outdoor Durability	Up to two (2) years depending on severity of exposure conditions	
Print Technology	All Inkjet: AQ, EcoSol, Solvent, Latex. Not recommended for most UV inks due to textured print surface.	
Standard Widths	54" x 150 ft - custom widths x length available by special order	

The information above is derived from internal testing by our company and based on information received from our suppliers. The values shown are for reference only, and are provided without guaranty and do not constitute a warranty, expressed or implied. The purchaser should determine, prior to use, the suitability of this material for his/her specific purpose. Data represents and average and is not intended for use as a specification.